

## 2.1.1 Modelling wax Special

**High quality elastic plate wax for the whole resin prosthetics. Composition based on a perfect combination of microwaxes, paraffin, natural waxes and bees' waxes. High edge and breaking stability as well as extremely low thermal contraction. It can be modelled and cut very well**

- the top-selling MORSA sheet wax
- made from the best raw materials - very high bees' wax content
- two different seasonal qualities for summer and winter
- two different sheet thicknesses 1.25 mm and 1.5 mm
- pleasant elastic quality during processing
- low degree of thermal contraction when cooling down
- no risk of unintentional changes in the set-up
- precise reproductive accuracy
- good wax-up characteristics
- high strength
- setting point: 59 °C for summer wax / ash content 0.002
- setting point: 57 °C for winter wax / ash content: 0.000
- sheet size: 175 x 80 x 1.25 mm and 175 x 80 x 1.5 mm
- available in 500 g / 2.500 g



**Order no. DM 000 106 VA 804**  
Summer 175 x 80 x 1.25 mm, 500 g

**Order no. DM 000 108 VA 804**  
Summer 175 x 80 x 1.50 mm, 500 g

**Order no. DM 000 102 VA 804**  
Summer 175 x 80 x 1.25 mm, 2.5 kg

**Order no. DM 000 104 VA 804**  
Summer 175 x 80 x 1.50 mm, 2.5 kg

**Order no. DM 000 107 VA 804**  
Winter 175 x 80 x 1.25 mm, 500 g

**Order no. DM 000 109 VA 804**  
Winter 175 x 80 x 1.50 mm, 500 g

**Order no. DM 000 103 VA 804**  
Winter 175 x 80 x 1.25 mm, 2.5 kg

**Order no. DM 000 105 VA 804**  
Winter 175 x 80 x 1.50 mm, 2.5 kg



## 2.1.5 Sheet wax Future

- Best quality wax, suitable for the entire range of prosthodontics
- high bees wax content
- two different sheet thickness 1.25 mm and 2 mm
- very cost-effective
- high strength
- setting point: 59° C / ash content: 0.004
- sheet size: 175 x 80 x 1.25 mm
- available in 500 g / 2.500 g



**Order no. DM 000 133 VA 804**  
175 x 80 x 1.25 mm, 500 g

**Order no. DM 000 134 VA 804**  
175 x 80 x 1.25 mm, 2.5 kg

**Order no. DM 000 135 VA 804**  
175 x 80 x 2.00 mm, 500 g

**Order no. DM 000 136 VA 804**  
175 x 80 x 2.00 mm, 2.5 kg



### 3.5 Cervical wax

- for accurately fitting margins
- ideal for edges of crowns due to stress free application and low setting shrinkage
- good adaptation
- available in the colours red and blue
- red: Setting point: 60 °C; Ash content: 0.035
- blue: Setting point: 64 °C; Ash content 0.02
- available in clip-clap tins of 65 g



**Order no. DR 000 119 HD 805**  
red, 65 g, tin

**Order no. DR 000 152 HD 805**  
red, 70 g, cylindre

**Order no. DR 000 120 HD 800**  
blue, 65 g, tin

### 3.7 Aesthetic wax

- burns without residue
- for understanding and fabricating wax patterns or teeth in their natural shape and colour
- low contraction
- good flowing and carving characteristics
- high surface density / opaque
- the exact waxed pattern is immediately recognisable
- the opaque colours enable the contours to be clearly visible
- available in four colours from ivory to brown
- ivory: Setting point: 82 °C; Ash content: 0.127
- cream: Setting point: 85 °C; Ash content 0.077
- light brown: Setting point: 85 °C; Ash content: 0.160
- brown: Setting point: 80 °C; Ash content 0.003
- available in clip-clap tins of 65 g
- available in cylindres of 70 g



**Order no. DR 000 123 HD 809**  
ivory, 65 g, tin

**Order no. DR 000 153 HD 809**  
ivory, 70 g, cylindre

**Order no. DR 000 124 HD 810**  
cream, 65 g, tin

**Order no. DR 000 125 HD 803**  
light brown, 65 g, tin

**Order no. DR 000 126 HD 801**  
brown, 65 g, tin